











4,30 mm / GLASS

	Reference standard	Test method	Reference value	Declared value
	Amount of water absorbed, in percentage	ISO-10545-3	-	0 %
	Resistance to abrasion of glazed tiles	ISO-10545-7	-	5 (test on Extra Light - White)
	Coefficient of thermal linear expansion	ISO-10545-8	-	9,1 *10 ⁻⁶ °C ⁻¹
	Glaze crazing resistance	ISO-10545-11	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to high concentrations of acids and alkali	ISO-10545-13	-	GLA - ULA
	Resistance to low concentrations of acids and alkali	ISO-10545-13	-	GHA - UHA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	-	GA - UA
	Resistance to staining	ISO-10545-14	-	5
	Colours resistance to fading	DIN-51094	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Barefoot slip resistance	DIN-51097	-	Cl. A + B + C